

## Product Data Sheet

### Description:

3300 FS Patch Kit is a three-component flooring system trowel applied at a minimum 1/4 inch thickness. 3300 FS is U.S.D.A. acceptable for food processing plants, and has excellent resistance to most acids, caustics, detergents and other corrosive materials. 3300 FS is excellent for patching or overlaying entire floor surfaces.

### ADVANTAGES:

- Prepackaged Easy To Use
- Excellent Adhesion
- Repair Mortar
- Quick Cure
- Easy To Clean, U.S.D.A. Acceptable
- Chemical Resistant
- Environmentally Safe.

### USES:

- Food Production Plants
- Forklift Aisle-ways
- Chemical Spill Containment Areas
- Industrial Production Facilities
- Warehouses

### SUPPLEMENTAL PRODUCTS:

- 3500 Grout - Pitching and Filler
- 3000 VS  
Vertical Surfaces and Coves
- 3000 FLEX  
Expansion Joint Filler

### PACKAGING AND COVERAGE:

**3300 FS Patch Kit** - covers approximately 16 square feet at ¼ inch (250 mils), and contains the following -

#### **1 mini-batch - 3300 - Primer –**

- 1 container – Part A (resin)
- 1 container – Part B (hardener)

#### **1 Batch - 3300 FS – Mortar -**

- 1 container – Part A (resin)
- 1 container – Part B (hardener)
- 37 pounds 3300 FS – Part C (chemical resistant aggregate)

### PROPERTIES:

<b>Compressive Strength (ASTM C-579) &lt;resin&gt;:</b>	11,500 psi	<b>Water Absorption (ASTM C-413):</b>	0.047%
<b>Tensile Strength (ASTM D-638) &lt;resin&gt;:</b>	1,700 psi	<b>Working Time at 75°F (24°C) (ASTM C-308):</b>	20-30 minutes
<b>Bond Strength (ASTM C-321):</b>	Greater than 350 psi; 100% concrete failure	<b>Shelf Life:</b>	1 Year
<b>Coefficient of Thermal Expansion:</b>	1.2 x 10 <sup>-5</sup> in./in./°F	<b>Solids Content</b>	By Weight: 100% By Volume: 100%
<b>Impact Strength:</b>	130 in. /lbs.	<b>Flexural Strength (ASTM C-580) &lt;resin&gt;:</b>	3,500 psi
<b>Indentation (MIL-D-3134F):</b>	No indentation	<b>Flammability:</b>	Does not support combustion
<b>Abrasion Resistance (ASTM D-1044):</b>	29 milligrams	<b>Colors:</b>	Red, Gray, Black

### SURFACE PREPARATION:

3300 FS Patch Kits may be installed only on clean, sound substrates.

#### Concrete:

New concrete must be cured a minimum of 28 days. All coatings, oils, grease and unsound concrete must be removed. Concrete surfaces must then be acid etched, scarified or shot blasted to remove surface laitance. A good bonding tooth, the texture of 60 grit sandpaper, is desired for maximum adhesion, with removal of all surface glaze.

#### Metal Surfaces:

Blast the surface to near white SSPC-SP10-70 or NACE No. 2 using a Venturi blast nozzle with 100 psi air. To produce the proper 4 mil anchor profile, the blast media should be properly graded, clean, sharp, and angular, similar to Humble Abrasive Flint #7 (6-30) mesh, or Steel Grit (HG25).

### MIXING:

Prior to starting, materials should be stored at 70°F (21°C) for at least 48 hours.

**Primer** - Empty entire contents of Part B into Part A and mix thoroughly for 2 minutes.

**Mortar** - Empty entire contents of Part B into Part A and mix thoroughly for 2 minutes. Slowly add the entire contents of Part C and mix for another 1-1/2 to 2 minutes.

As with all two-component systems, apply immediately after mixing, as heat is generated from the exothermic reaction over time and the working time of the mortar will substantially be reduced if the material is left in a pail.

**APPLICATION:**

Substrate temperature should be 65°-85°F (18°-29°C) during installation and 96 hours thereafter for complete cure. Do not apply 3300 FS when floor temperature is below 60°F (16°C). Pour the entire batch onto the floor as soon as blended and trowel smooth with a steel trowel. After troweling the mortar, wipe your trowel with M.E.K. or Denatured Alcohol and swipe surface. This will reduce trowel drag and allow for a tighter finished surface.

**CURE TIME:**

3300FS will harden to foot traffic in 6-8 hours at 75°F (24°C). Maximum chemical resistance will occur after 96 hours of cure time at 75°F (24°C).

**CLEANUP:**

Cured or hardened 3300FS will bond to practically all surfaces and is extremely difficult to remove. Clean all tools and mixer immediately after use with acetone or other solvent based cleaners.

**SAFETY:**

Avoid skin contact. If eye contact occurs, flush with water and consult a physician immediately. Keep work areas well ventilated. Never seal a container of mixed Part A and B as the continuing exothermic reaction may cause the container to explode. 3300FS Material Safety Data Sheets are available upon request.

**NOTE:**

Refer to 3300 FS Instruction for use.

**Limited Warranty**

Milamar Coatings products are manufactured to be free of defects in material and workmanship in meeting the properties specified on its individual Product Data Sheets. Users and installers of Milamar Coatings products are solely responsible for determining the suitability of the products for specific product applications. Milamar Coatings makes no Warranty or Guarantee, express or implied, including warranties of fitness, design compatibility or merchantability, for any particular use and shall have no responsibility or liability, including direct, indirect or consequential damages, due to injury, delay or third party claims for installation or repair. Likewise, Milamar Coatings assumes no liability of any nature for products that are adjusted in the field or that do not utilize all specified Milamar Coatings components. Should any Milamar Coatings product be proved to be defective within one year from the date of shipment, Milamar Coatings will, at its sole discretion, replace the material; issue a credit to the customer's account; or provide a cash refund for the initial, paid purchase price of the material. Potential claims regarding product quality must be received in writing by Milamar Coatings within 30 days of the discovery of such potential defect. This Warranty is exclusive of all other warranties, expressed or implied, and may only be adjusted in writing, signed by an officer of Milamar Coatings, L.L.C

**Milamar Coatings, L.L.C.**

www.milamar.com

311 NW 122nd Street, Ste. 100

Oklahoma City, OK 73114

Ph.: 405.755.8448

Fax: 405.755.8450