

	%	Temp. (Fahrenheit)	Flooring Systems												Lining / Coating Systems									
			1000CS	Drescoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS			
Acetic Acid	10.0%	75	2	2	2	2	2	3	2	1	1	1		2	1	1	1	1	1	1	1	1	1	1
Acetic Acid	10.0%	150								2	1	1	1		2	2	2	2	2	2	2	1	1	1
Acetic Acid	20.0%	75	3	3	3	3	3		2	1	1	1		3	2	2	2	1	1	1	1	1	1	1
Acetic Acid	20.0%	150								2	2	1			3	2		2	2	2	2	1	1	1
Acetic Acid	50.0%	75	3	3	3	3	3		2	1	1	1		3				1	1	1	1	1	1	1
Acetic Acid	85.0%	75								3	3	2						3	3	3	2	2	2	2
Acetic Acid	Glacial	75			4	4	3		4	4	3	2			4	2	2	4	4	3	2	2	2	2
Acetic Anhydride		100								4	3	2			3	2		4	4	3	2	2	2	2
Acetone		75	3	3				3		4	4	2		3	2			4	4	4	2	2	2	2
Acetonitrile		75										2										2	2	2
Acetophenone		75			4	4	3		4	4	2	2						4	4	2	2	2	2	2
Acrylic Acid	Glacial	100									2	1			3					2	1	1	1	1
Acrylic Acid	5.0%	100								1	1	1						1	1	1	1	1	1	1
Acrylic Acid	20.0%	100								2	1	1						2	2	1	1	1	1	1
Acrylic Acid	50.0%	75						2				2										2	2	2
Acrylic Acid	Esterfied	100										1			2							1	1	1
Acrylonitrile		75	3		4	4	3		4	3	3	2		3	2	2		3	3	3	2	2	2	2
Adipic Acid	Sat.	75			2	2	2		2	2		1			1			2	2			1	1	1
Aluminum Ammonium Sulfate	50.0%	100								1					1	1		1	1					
Aluminum Chloride	5.0%	75			2	2	2		2	1	1	1			1			1	1	1	1	1	1	1
Aluminum Chloride	15.0%	120								1	1	1						1	1	1	1	1	1	1
Aluminum Chloride	25.0%	75			2	2	2		2	1	1	1			1			1	1	1	1	1	1	1
Aluminum Chloride	29.0%	150								1	1	1						1	1	1	1	1	1	1
Aluminum Chloride	32.0%	210								2	2	2						2	2	2	2	2	2	2
Aluminum Fluoride	5.0%	100								2	2	1			1			2	2	2	1	1	1	1
Aluminum Fluoride	10.0%	100								2	2	2			1			2	2	2	2	2	2	2
Aluminum Fluoride	20.0%	100								2	2	2			1			2	2	2	2	2	2	2
Aluminum Nitrate	50.0%	75			2	2	2		2	1		1			1			1	1			1	1	1
Aluminum Potassium Sulfate	Sat.	75			2	2	2		2	1	1	1						1	1	1	1	1	1	1
Aluminum Sulfate	5.0%	75			2	2	2		2	1	1	1						1	1	1	1	1	1	1
Aluminum Sulfate	8.0%	150								1	1	1			1	1	1	1	1	1	1	1	1	1
Aluminum Sulfate	50.0%	150								1	1	1			1	1	1	1	1	1	1	1	1	1
Ammonia	25.0%	75						2																
Ammonium Chloride	50.0%	100								1	1	1			1			1	1	1	1	1	1	1
Ammonium Chloride	Sat.	75			2	2	2		2	1	1	1						1	1	1	1	1	1	1
Ammonium Hydroxide	29.0%	75	2	2	1	1	1		2	1	3	1		2	1	1	1	1	1	3	1	1	1	1
Ammonium Lignin Sulfonate	52.0%	150										1			2							1	1	1
Ammonium Nitrate	5.0%	75	2	2						1	1	1						1	1	1	1	1	1	1
Ammonium Nitrate	50.0%	75			2	2	2		2	1	1	1		2				1	1	1	1	1	1	1
Ammonium Perchlorate	10.0%	150								1								1	1					
Ammonium Persulfate	10.0%	100								1	1	1			1		1	1	1	1	1	1	1	1
Ammonium Persulfate	10.0%	150								2	2	2			2	1		2	2	2	2	2	1	1
Ammonium Phosphate (Monobasic)	50.0%	75			2	2			2	1	2	1						1	1	2	1	1	1	1

1 = Continuous long term exposure
 2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
 4 = Not recommended for direct contact

	%	Temp. (Fahrenheit)	Flooring Systems												Lining / Coating Systems							
			1000CS	Dresscoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS	
Ammonium Sulfate	46.0%	150							1	1	1				1			1	1	1	1	1
Ammonium Sulfate	50.0%	75			2	2	2		1	1	1				1	1	1	1	1	1	1	1
Aniline		75						3	4	4	2				4	4	4	2	2	2	2	2
Aniline Hydrochloride		75			2	2			2	1	1				1	1		1	1	1	1	1
Aromatic 100		75			2	2	2		2	1	1				1	1		1	1	1	1	1
Benzaldehyde		75			4	4			4	4	4	3			4	4	4	3	3	3	3	3
Benzene		75	2	2	3	3	2		4	3	3	1		2	2	2	2	3	3	3	1	1
Benzene 50%, Gasoline 45%, MTBE 5%		100										1									1	1
Benzene Sulfonyl Chloride		75			2	2					2			2				2	2		2	2
Benzyl Peroxide		100												1								1
Benzyl Peroxide 10%, Sodium Hydroxide 5%		100										2		1		1					2	2
Boric Acid	25.0%	75			2	2	2		2	1	1	1			1	1	1	1	1	1	1	1
Bromine (gas)		75										1									1	1
Bromine (liquid)		75							3	3	3										3	3
Butyl Acetate - N		75	2	2				2	3	3	2				3	3	3	2	2	2	2	2
Butyl Alcohol - N		75	3	3					2	2	1				2	2	2	1	2	1	2	2
Butyl Alcohol - N		100	1						3	2	1		1		3	3	2	1	1	1	1	1
Butyl Carbitol		100							4	2	1				4	4	2	1	1	1	1	1
Butyl Cellosolve		100							1	2	1				1	1	2	1	1	1	1	1
Butyrolactone		75					2				2			1						2	2	2
Calcium Carbonate	Sat.	75							1		1				1	1	1		1	1	1	1
Calcium Chloride	25.0%	75	2	2			2		2	1	1	1			1	1	1	1	1	1	1	1
Calcium Chloride	50.0%	75							1	1	1		1		1	1	1	1	1	1	1	1
Calcium Chloride	Sat.	75					2		2	1	1	1		1		1	1	1	1	1	1	1
Calcium Hydroxide	50.0%	75			2	2	2	2	1		1				1	1		1	1	1	1	1
Calcium Hydroxide	50.0%	150							2		2			1	1	1	2	2		2	2	2
Calcium Hydroxide	Sat.	75	2	2	3	3	2		3		1									1	1	1
Calcium Hypochlorite	5.0%	75			2	2	2		2	1	1	1			1	1	1	1	1	1	1	1
Calcium Hypochlorite	50.0%	100							1	1	2			1	1	1	1	1	1	2	2	2
Calcium Hypochlorite	50.0%	150							3	3	2			2		3	3	3	2	2	2	2
Carbon Disulfide		75			2	2	2				2									2	2	2
Chloroacetic Acid (Monochloroacetic Acid)	80.0%	75			4	4	4		2	3	2			3	3		3	3		2	2	2
Chlorothene	99.0%	100								4	2			3				4	2	2	2	2
Chromated Copper Arsenate	3.0%	75	2	2	2	2			2	2	1			1	1	1	2	2		1	1	1
Chromated Copper Arsenate	4.0%	75	2	2	2	2			2		1			1	1	1				1	1	1
Chromated Copper Arsenate	4.0%	150			2	2			2		2			1	1	1				2	2	2
Chromated Copper Arsenate	10.0%	75	2	2	2	2			2		1			1	1	1				1	1	1
Chromated Copper Arsenate	10.0%	150			2	2			2		2			1	1	1				2	2	2
Chromated Copper Arsenate	50.0%	75	2	2	2	2			2		1			1	1	1				1	1	1
Chromic Acid	1.0%	75			2	2	2		2	1	1	1			1	1	1	1	1	1	1	1
Chromic Acid	5.0%	100							2	1	1			1		2	2	1	1	1	1	1
Chromic Acid	10.0%	75			2	2	2		2	2	1	1		2	1	1	1	2	2	1	1	1
Chromic Acid	10.0%	150							2	1	2			2		2	2	1	2	2	2	2

1 = Continuous long term exposure
 2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
 4 = Not recommended for direct contact

	%	Temp. (Fahrenheit)	Flooring Systems												Lining / Coating Systems							
			1000CS	Dresscoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS	
Chromic Acid	20.0%	100			3	3	2			2	1	2			2	2		2	2	1	2	2
Chromic Acid	20.0%	150									2	2			3				2	2	2	2
Chromic Acid	50.0%	75	3	3	3	3	3		3	4	2	3		3	3	3		4	4	2	3	3
Citric Acid	20.0%	75	2	2	2	2	1	2	1	1	1	1		2	2	1		1	1	1	1	1
Citric Acid	50.0%	75	2	2	2	2	2		2	1	1	1		1	1	1	1	1	1	1	1	1
Copper Sulfate	50.0%	150								1	1	1			1	1	1	1	1	1	1	1
Copper Sulfate	Sat.	75			2	2	2		2	1	1	1					1	1	1	1	1	1
Corn Oil		75			2	2	2		2	1	1	1					1	1	1	1	1	1
Cresol		75						3														
Creosote Oil		75			2	2	2									2					3	3
Cresylic Acid		100								4					2	2		4	4			
Cumene		100										2									2	2
Cupric Chloride	5.0%	150								1		1						1	1		1	1
Cupric Chloride	20.0%	150								1		1						1	1		1	1
Cupric Chloride	50.0%	150								1		1						1	1		1	1
Cyclohexane		75			2	2	2		4	1	1	1						1	1	1	1	1
Diesel Fuel		75	1	2						1	1	1		1				1	1	1	1	1
Diethanolamine		75	2	2	2	2	2		2	2	2	1		2	3	2	2	2	2	2	1	1
Diethanolamine		100								2	2	1						2	2	2	1	1
Diethylenetriamine		75			3	3	2		4	4	4	3			3	2		4	4	4	3	3
Dimethyl Disulfide		75					2		4			4									4	4
Dimethylacetamide		75					3		4		4	4			4					4	4	4
Dimethylformamide	20.0%	75										2									2	2
Dimethylformamide		75			4	4	4			4	4	3		4	4	4		4	4	4	3	3
Dodecylbenzene		130								2		2						2	2		2	2
Dodecylbenzene Sulfonic Acid		75			2	2	2			1		1						1	1		1	1
Dodecylbenzene Sulfonic Acid		150								2		2						2	2		2	1
Epichlorohydrin		75			4	4	3		4	3		2				3		3	3		2	2
Ethanolamine (Monoethanolamine)	10.0%	100										1			1	1	1				1	1
Ethanolamine (Monoethanolamine)		75	3	3	3	3	3		3	3	2	1		3	3	3	3	3	3	3	1	1
Ethanolamine (Monoethanolamine)		100								3	3	2			2	2		3	3	3	2	2
Ethyl Acetate		75								4	4	2		3				4	4	4	2	2
Ethyl Alcohol		75	2	2	2	2	2		3	3	2	1		2	1	1	1	3	3	2	1	1
Ethyl Alcohol		100								4	2	1		2	1	1	1	4	4	2	1	1
Ethyl Alcohol		150									4	2			2	1				4	2	2
Ethyl Benzene		100								3	3	1						3	3	4	1	1
Ethyl Benzene		150										3							4		3	3
Ethylene Diamine		75										2									2	2
Ethylene Dichloride (Dichloroethane)		75			4	4	4		4	4		2			4	4		4	4		2	2
Ethylene Glycol		75			1	1	1		2	1	1	1		1	1	1	1	1	1	1	1	1
Ethylene Glycol		200								2	2	1						2	2	2	1	1
Ethylene Glycol Butyl Ether (Butyl Cellosolve)		100								2	2	1			1	1	1	2	2	2	1	1
Ethylene Glycol Ethyl Ether (Cellosolve)		100										1			2	1					1	1

1 = Continuous long term exposure
 2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
 4 = Not recommended for direct contact

Chemical Resistance Guide

	%	Temp. (Fahrenheit)	Flooring Systems										Lining / Coating Systems									
			1000CS	Dresscoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS	
Hydrofluoric Acid	49.0%	75	3	2								2*								2*	2*	
Hydrofluoric Acid	55.0%	100										2*		2						2*	2*	
Hydrofluorosilicic Acid	20.0%	100							3	2	1	2		1			2	2	1	2	2	
Hydrogen Peroxide	3.0%	75			2	2			2	1	2	1		2	2			1	1	2	1	1
Hydrogen Peroxide	30.0%	75	3	3	2	2		2	2	2	2	2		2			2	2	2	2	2	
Hydrogen Peroxide	70.0%	75			3	3			2	2	3	2		3				2	2	3	2	2
Isopropyl Alcohol		75	2	2								2	1							2	1	1
Isopropyl Alcohol		150										3	2							3	2	2
Jet Fuel		75	1	2	1	1	1		2	2		1		1	1	1	2	2		1	1	
Kerosene		100						2			1	1		1	1	1			1	1	1	
Kerosene		150							2	2	1			1	1	1	2	2	2	1	1	
Lactic Acid	2.0%	150								1	1	1		1	1	1	1	1	1	1	1	
Lactic Acid	8.5%	75	2	2	2	2	2	2	2	1	1	1		2	2			1	1	1	1	1
Lactic Acid	10.0%	150						3		1	1	1		2	2	2		1	1	1	1	1
Lactic Acid	85.0%	75	3	2	2	2	2		2	1	1	1		3	3	2		1	1	1	1	1
Lard		150													1							
Lignin - Norlig - A		75			2	2	2		2	2		1		2	2			2	2		1	1
Liquor - Black		75			2	2			2	2		1						2	2		1	1
Liquor - Black		205													1							
Liquor - Black (Sulfate Process - Thilmany)		185												2		2						
Liquor - Black (Sulfite Process -- Modified - pH 4.76)		170													2							
Liquor - Black (Weak P & G)		100								1								1	1			
Liquor - Black (Weak P & G)		150								1								1	1			
Liquor - Black (Weak Mead Paper)		200													2	2						
Liquor - Black (Weak)		205													2							
Liquor - Black (Weak - Sulfite Process - P & G)		75			2	2	2		2	2		1				2		2	2		1	1
Liquor - Black (Weak - Sulfite Process - P & G)		205													2							
Liquor - Brown		75			2	2	2		2	2		1						2	2		1	1
Liquor - Green (Sulfate Process - Thilmany)		185														2						
Liquor - White		75			2	2			2	2		1						2	2		1	1
Liquor - White		220													2	2						
Magnesium Bisulfite		190														2						
Magnesium Chloride	10.0%	75			2	2			2	1	1	1						1	1	1	1	1
Magnesium Hydroxide		75			2	2	2		2	1		2						1	1		2	2
Maleic Acid	50.0%	150								2	2	2		3				2	2	2	2	2
Methacrylic Acid	5.0%	100								1	2	1						1	1	2	1	1
Methacrylic Acid	5.0%	150									3								2	3		
Methacrylic Acid	50.0%	150									3	3			3	2				3	3	3
Methanesulfonic Acid	70.0%	75							2			2									2	2
Methanesulfonic Acid	70.0%	100							2			2									2	2
Methyl Acetate		100								4		2						4	4		2	2
Methyl Alcohol	30.0%	75									2	1								2	1	1
Methyl Alcohol		75	3	3	3	3	2	3	3	4	2	1		2	3	2		4	4	2	1	1

1 = Continuous long term exposure
 2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
 4 = Not recommended for direct contact

	%	Temp. (Fahrenheit)	Flooring Systems																			
			1000CS	Drescoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	Lining / Coating Systems	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS
Phosphorus Acid	70.0%	75			2	2	2			1		1			2	2	2	1	1		1	1
Potassium Carbonate	50.0%	75			1	1	1		2	1	1	1		1	1	1		1	1	1	1	1
Potassium Chloride	45.0%	150								1	1	1					1	1	1	1	1	1
Potassium Chloride	50.0%	75			1	1	1		2	1	1	1		1	1		1	1	1	1	1	1
Potassium Dichromate	10.0%	75						2		1	1	1					1	1			1	1
Potassium Hydroxide	1.0%	75	2	2						1	1	1						1	1	1	1	1
Potassium Hydroxide	10.0%	150								2		2					1	1	1	2	2	2
Potassium Hydroxide	20.0%	75			1	1	1	3	2	1		1		1	1	1	1	1	1		1	1
Potassium Hydroxide	45.0%	150								2							1	1				
Potassium Hydroxide	50.0%	75			1	1	1		2	1		1				1	1	1	1	1		1
Potassium Hydroxide	65.0%	100								1						1	1	1	1	1		
Potassium Hydroxide 44%, Acrylic Acid 21%		100													1							
Potassium Permanganate	5.0%	150								2	2	1						2	2	2	1	1
Potassium Phosphate	10.0%	75			2	2			2	2		2						2	2		2	2
Potassium Sulfite	45.0%	100								1								1	1			
Propionaldehyde		75										3									3	3
Propionic Acid	5.0%	100								1		1						1	1		1	1
Propionic Acid		75			4	4			4			1									1	1
Propyl Acetate - N		75										2									2	2
Propyl Aldehyde - N		75										2									2	2
Propylene Glycol Methyl Ether (PM)		75	3	2	3	3	2		3	3		2		3	3	2		3	3		2	2
Pyradine		100									4	3								4	3	3
Sodium Bisulfide	35.0%	100								1	1	1		1	1	1		1	1	1	1	1
Sodium Bisulfite	35.0%	100								1	1	1						1	1	1	1	1
Sodium Bisulfite	40.0%	150								2	2	1						2	2	2	1	1
Sodium Bisulfite	50.0%	75			2	2			2	1	1	1						1	1	1	1	1
Sodium Carbonate	5.0%	75			1	1			2	1	1	1		1	1			1	1	1	1	1
Sodium Carbonate	50.0%	75				1			2	1	1	1			2			1	1	1	1	1
Sodium Chlorate	25.0%	75			2	2			2	1	1	1						1	1	1	1	1
Sodium Chlorate	48.0%	200								2	2	2			2	2		2	2	2	2	2
Sodium Chlorate	50.0%	75					2		2	1	1	1		2		2		1	1	1	1	1
Sodium Chloride	25.0%	150								1	1	1						1	1	1	1	1
Sodium Chloride	30.0%	75					2			1		1						1	1		1	1
Sodium Chloride	50.0%	75	1	2			2		2	1	1	1		2		2		1	1	1	1	1
Sodium Chloride	Sat.	150								1	1	1			1			1	1	1	1	1
Sodium Chloride	Sat.	200								2	2	2			1	2		2	2	2	2	2
Sodium Chloride 20%, Sodium Hydroxide 9%, Sodium Hypochlorite 5ppm		150								2								2	2			
Sodium Chloride 20%, Sodium Hydroxide 9%, Sodium Hypochlorite 5ppm		180								2								2	2			
Sodium Formate	60.0%	200										1									1	1
Sodium Hydrosulfide	5.0%	75			2	2			2	1	1	1						1	1	1	1	1

1 = Continuous long term exposure
 2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
 4 = Not recommended for direct contact

	%	Temp. (Fahrenheit)	Flooring Systems												Lining / Coating Systems							
			1000CS	Dresscoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS	
Sodium Hydrosulfide	25.0%	75							2	1	1	1						1	1	1	1	1
Sodium Hydrosulfite	40.0%	100								2		1						2	2		1	1
Sodium Hydroxide	1.0%	75	1	1	1	1	1		2	1		1		1	1	1	1	1	1	1	1	1
Sodium Hydroxide	5.0%	100								1		1		1				1	1		1	1
Sodium Hydroxide	5.0%	150								2		2		1	1	1		2	2		2	2
Sodium Hydroxide	10.0%	75			1	1	1		2	1		1			1			1	1		1	1
Sodium Hydroxide	10.0%	150								2		2			1	1		2	2		2	2
Sodium Hydroxide	10.0%	200								3		3			2	2		3	3		3	3
Sodium Hydroxide	20.0%	75	1	1	1	1	1		2	1		1			1			1	1		1	1
Sodium Hydroxide	25.0%	150								2		2		2	1	2		2	2		2	2
Sodium Hydroxide	44.0%	75	1	1						1		1						1	1		1	1
Sodium Hydroxide	50.0%	75	1	1	1	1	1		2	1		1		1	1	1	1	1	1		1	1
Sodium Hydroxide	50.0%	180								2		3			1	2		2	2		3	3
Sodium Hydroxide 22%, Sodium Chloride 12%		200													2							
Sodium Hypochlorite	5.3%	75			1	1	1		2	1	2	1		2	1	1	1	1	1	2	1	1
Sodium Hypochlorite	5.3%	150								2	3	2				2		2	2	3	2	1
Sodium Hypochlorite	12.0%	75			2	2	2			1	2	1		2	1	1		1	1	2	1	2
Sodium Hypochlorite	12.0%	150								3					2			3	3			
Sodium Hypochlorite	12.5%	100								2	3	2						2	2	3	2	2
Sodium Hypochlorite	50ppm	100								1	1	1						1	1	1	1	1
Sodium Hypochlorite	200ppm	180								3	2	2						3	3	2	2	2
Sodium Hypochlorite - (Sno-Glo Bleach)		70								1		1			1			1	1		1	1
Sodium Sulfate	Sat.	75					2		2	1	1	1				2		1	1	1	1	2
Sodium Vinyl Sulfonate		100								1		1						1	1		1	1
Stannous Chloride	10.0%	150								1	1	1			1			1	1	1	1	1
Stannous Chloride	55.0%	150								1	1	1			2			1	1	1	1	1
Styrene		75	3	2	3	3	2		3	2	3	1		3	3	2		2	2	3	1	1
Sulfamic Acid	20.0%	150								2	2	2			2	2		2	2	2	2	2
Sulfuric Acid	1.0%	75			1	1	1		2	1	1	1		1	1	1	1	1	1	1	1	1
Sulfuric Acid	5.0%	75	1	1	1	1	1			1	1	1		1	1	1	1	1	1	1	1	1
Sulfuric Acid	5.0%	150								1	1	1			1	1	1	1	1	1	1	1
Sulfuric Acid	10.0%	75			1	1	1		2	1	1	1		1	1		1	1	1	1	1	1
Sulfuric Acid	10.0%	150								1	1	1		3				1	1	1	1	1
Sulfuric Acid	20.0%	75	2	2	1	1	1		2	1	1	1		2	1	1	1	1	1	1	1	1
Sulfuric Acid	25.0%	150								1	1	1			1			1	1	1	1	1
Sulfuric Acid	30.0%	75								1	1	1		1	1	1	1	1	1	1	1	1
Sulfuric Acid	40.0%	100								1	1	1		2				1	1	1	1	1
Sulfuric Acid	40.0%	150								1	2	1			1	1	1	1	1	2	1	1
Sulfuric Acid	50.0%	75	2	2	2	2	1	2	2	1	1	1		2	2	1	1	1	1	1	1	1
Sulfuric Acid	50.0%	150								2	2	1			2	1	1	2	2	2	1	1
Sulfuric Acid	70.0%	100			2	2	1			1	1	1			2	1	1	1	1	1	1	1
Sulfuric Acid	70.0%	150								2	2	2			2			2	2	2	2	2
Sulfuric Acid	75.0%	100			2	2	1		2	2	1	1			2	1	1	2	2	1	1	1

1 = Continuous long term exposure
 2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
 4 = Not recommended for direct contact

Chemical Resistance Guide

	%	Temp. (Fahrenheit)	Flooring Systems												Lining / Coating Systems							
			1000CS	Dresscoat	3100FS/3200FS	3300FS/3300PT	3300CR	4410UR/4420UR	5000FS	6000FS	6100FS	6200FS	2300LS	2600LS	2620CR	2900LS	6600LS	6650CS	6700LS	6800LS	6850LS	
Sulfuric Acid	77.7%	150					2			3	2	2			2	2		3	3	2	2	2
Sulfuric Acid	80.0%	100					1			3	2	2			3	1		3	3	2	2	2
Sulfuric Acid	80.0%	150					2			4	3	3			3	2	2	4	4	3	3	3
Sulfuric Acid	86.0%	75	3	3			2			4	3	2			3	2		4	4	3	2	2
Sulfuric Acid	90.0%	100					2			4	4	3			3	2	2	4	4	4	3	3
Sulfuric Acid	98.0%	75			4	4	2		4	4	4	3			4	2	3	4	4	4	3	3
Sulfuric Acid - Fuming	20.0%	100													1	1						
Sulfuric Acid - Heptane - Water - Oil		75								1		1			1			1	1		1	1
Sulfuric Acid - Oleum Solution		120														1						
Sulfuric Acid 49%, Nitric Acid 35%		75					3				3	4				4				3	4	4
Sulfurous Acid	10.0%	100								1	1	1						1	1	1	1	1
Tall Oil		75			2	2	2		2	1	1	1		2		2		1	1		1	1
Tall Oil		180								2		1			2	2	2	2	2		1	1
Tartaric Acid	10.0%	75						2		1		1						1	1		1	1
Tetrahydrofuran (THF)		75			4	4	3		4	3		2				3	3	3	3		2	2
Texanol		75			2	2	2		2	2		1					2	2			1	1
Toluene		75	2	2	2	2	1		4	3	3	1		2	2	1	1	3	3	3	1	1
Toluene (2,4) Diisocyanate (Des N-75)		100								3	2	2						3	3	2	2	1
Toluenesulfonic Acid-(p)	75.0%	100								1	2	1						1	1	2	1	1
Tributyl Phosphate		100													2							
Trichloroethane 1,1,1 (Chloroethane)		75			2	2	1		3	2		1		2	2	1	1	2	2		1	1
Trichloroethylene		75								3		2						3	3		2	2
Trimethyl Sulfonium Chloride		100								1		1						1	1		1	1
Urea		75			1	1	1		2	1	1	1		1	1	1	1	1	1	1	1	1
Urea	50.0%	100								1	1	1						1	1	1	1	1
Urea Ammonium Nitrate		125								1		1						1	1		1	1
Water - DI		150								1	2	1		2	1	1	1	1	1		1	1
Xylene		100								2	2	1			1	1	1	2	2	2	1	1
Xylene		150								3	3	2			2	2		3	3	3	2	2
Zinc Chloride	40.0%	150								1	1	1			1			1	1	1	1	1

* Double Veil Coat => 30 mil system

Revised 11/08

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact

SCM

1 = Continuous long term exposure
2 = Short term exposure (< 72 hours)

3 = Splash and Spill (< 8 hours)
4 = Not recommended for direct contact